
# 'acoufelt



# QuietForm Wall Panels

Premier Collection

The QuietForm<sup>™</sup> panel is a thermal-molded acoustic solution that combines striking three-dimensional wall designs with transformative soundscaping functionality. Available in a wide spectrum of Premier color options, QuietForm panels can be effortlessly installed over any existing wall surface. With a variety of designs to choose from and the flexibility to rotate panels for unique patterns, QuietForm empowers creativity while enhancing both aesthetics and acoustic performance.

# Specifications

Surface	Wall		
Material	FilaSorb <sup>™</sup> polyester felt		
Thickness	1/2", 8mm (±10%) range to 1", 24mm (±10%)		
Weight	0.49 lb./ft²(±10%) 0.98 lb./ft²(±10%)		
Standard Sizes	48" W x 110" H Geometry pattern, 108" H		



QuietForm Wall Panel with Celestial A Pattern in Eucalyptus

# Technical

NRC Rating	<b>12mm</b> 0.45, no air gap 0.60, 20mm air gap 0.75, 50mm air gap <b>24mm</b> 0.60, no air gap
Fire Test	ASTM E84, Class A Flame spread index: 15 Smoke developed index: 200
Water Sorption	ASTM C1104-2019 (A Modified) Water sorbed by weight: 0.20% (based on a 12mm thick panel)
Colorfastness	ISO 105-B02, 6-7

## Details

Lead Time	3 – 6 weeks
Origin	Manufactured and assembled in the US
<u>Warranty</u>	Product: 20 years* Colorfastness: 20 years*

\* Conditions apply

# Environmental

<b>Recycled Content</b>	Minimum 60%		
Energy	Generated using 40% solar energy		
Indoor Air Quality	VOC less than/equal to 0.5mg/m3		
Recyclable	100%*		
Certifications	Health Product Declaration (HPD)**		
	Declare Certification - LBC Red List Free		
	(third-party verified)		
	SCS Global Indoor Advantage Gold		

\* PET is recyclable through participating partners.

\*\* HPD only applies to 12mm thickness.



® The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

# Colorways

#### PREMIER


White WH12	Almond AL55	<b>Celery</b> CE65	<b>Sencha</b> SE58	Metal ME03	<b>Flamingo</b> FL61	<b>Quartz</b> QU67	<b>Turmeric</b> TU60
<b>Platinum</b> PL04	<b>Pearl</b> PE21	<b>Pistachio</b> PI25	<b>Thistle</b> TH28	<b>Stonewash</b> ST72	<b>Amethyst</b> AM69	<b>Valentine</b> VA70	<b>Wheat</b> WH68
<b>Grey</b> GR02	<b>lvory</b> IV11	<b>Eucalyptus</b> EU71	<b>Peacock</b> PE20	<b>Periwinkle</b> PE23	<b>Lilac</b> LI13	<b>Peach</b> PE19	<b>Popcorn</b> PO26
<b>Slate</b> SL27	<b>Umber</b> UM54	<b>Wasabi</b> WA29	<b>Sea Salt</b> SE57	<b>Marine</b> MA15	<b>Berry</b> BE06	<b>Peppercorn</b> PE22	<b>Carrot</b> CA08
<b>Charcoal</b> CH01	<b>Walnut</b> WA56	<b>Oregano</b> OR18	<b>Azure</b> AZ05	<b>Iris</b> IR10	<b>Flint</b> FL64	<b>Shiraz</b> SH63	<b>Currant</b> CU59
Piano Black	Midnight	Kalo	Depim	Granita			
<b>Piano Black</b> PI24	<b>Midnight</b> MI16	Kale KA12	<b>Denim</b> DE09	<b>Granite</b> GR62			

Order samples at **acoufelt.com/colorways** 



# Sizes

Standard Sizes	48" W x 110" H
	Geometry pattern, 108" H
Thickness	1/2", 8mm (±10%) range to 1", 24mm (±10%)




Ø

# How to Specify

1. Choose Panel Pattern

2. Choose Colorways

Select desired panel pattern. See recommended layouts for larger designs.



1. Choose Panel Pattern


2. Choose Colorways


See colorways on page 3.



# **Mounting Methods**

#### **Construction adhesive**






\* For wall mount applications only.

### **Acoustic Performance**

Test Method	ISO 354-2006
Install Method	A
Rating Method	ISO 11654-2002
Test Results	NRC 0.45, no air gap NRC 0.60, 20mm air gap NRC 0.75, 50mm air gap SAA 0.43, no air gap SAA 0.61, 20mm air gap SAA 0.72, 50mm air gap



#### What is a Noise Reduction Coefficient (NRC)?

You'll find the NRC rating in the specifications of all of our products. This acronym stands for Noise Reduction Coefficient, and is expressed as a single number, a rating that describes the degree to which acoustic products can absorb sound. You can use NRC values to understand the overall performance of our acoustic wall and ceiling products. The higher the NRC, the better the product is at soaking up the sound.

Performance Indices: Noise Reduction Coefficient (NRC) results represent the absorption coefficients measured at the one third octave bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customization of installation of the product could alter the results. Sound Absorption Average (SAA) indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz.

